

ONTARIO QC

M·PROTECT

Sestava Composition Sirovinski sastav Zusammensetzung Composizione	100% Poliester 100% Polyester 100% Poliester 100% Polyester 100% Poliestere	Širina Width Širina Breite Altezza	140 cm ± 2%	Teža Weight Težina Gewicht Peso	360 g/m² ± 5%
--	---	--	--------------------	---	----------------------

TEST	STANDARD	REZULTATI / RESULTS / REZULTATI / ERGEBNISE / RISULTATI	
		Osnova / Warp / Osnova / Kette / Ordito	Votek / Weft / Potka / Schuss / Trama
Raztezna trdnost Tensile strength Čvrstoća na rastezanje Zugfestigkeit Resistenza alla trazione	DIN EN ISO 13934-1	1206 N	1624 N
Raztržna trdnost Tear growth strenght Čvrstoća na kidanje Weiterreissfestigkeit Resistenza alla lacerazione	DIN EN ISO 13937-3	142,0 N	147,2 N
Drsnost niti Resistance to seam slippage Otpornost na pomjeranje / pomeranje šava Nahtschiebewiderstand Resistenza allo scorrimento della cucitura	DIN EN ISO 13936-2 pri / at / kod / bei / a 180 N	2,7 mm	2,2 mm
Obstojnost barve na drgnjenje Colour fastness to rubbing Postojanost boje na trljanje Reibechtheitheit Resistenza del colore all'abrasione	EN ISO 105-X12	Suho / Dry / Suvo / Trocken / Secco 4-5	Mokro / Wet / Mokro / Nass / Umido 4-5
Obstojnost barve na svetlobo Colour fastness to light Postojanost boje na svjetlo/svetlost Lichtechtheit Resistenza del colore alla luce	DIN EN ISO 105-B02 Process 3 Exposure Level 5	5	
Obstojnost tkanine na drgnjenje Abrasion resistance Postojanost tkanine na trljanje Scheuerbestaendigkeit Resistenza alla lacerazione	DIN EN ISO 12947-1 DIN EN ISO 12947-2	>100.000 obratov / Revs. / obrtaja / Touren / giri	
Piling Piling Resistance Piling Pillbildung Resistenza al pilling	DIN EN ISO 12945-2 5.000 obratov Revs. / obrtaja Touren / giri	4-5	

AZO barvila AZO dyes AZO boja AZO Farbstoffe Coloranti azoici	DIN EN 14362-1 DIN EN 14362-3	
Alergena in karcenogena barvila Allergenic and carcinogenic dyes Alergene i kancerogene boje Allergisierende und krebserregende farbstoffe Coloranti allergenici e cancerogeni	DIN 54231	Ni zaznano Not detectable Ne sadrži Nicht nachweisbar Non rilevabile
Formaldehid Formaldehyde Formaldehyd Formaldehyd Formaldeide	DIN EN ISO 14184-1	
Test negorljivosti Fire Retardant Test negorivosti Flammhemmend Ignifugo	BS 5852 source 0 DIN EN 1021-1 without soaking	Prestal Passed Prošao Ueberstanden Superato
Odpornost proti prepuščanju tekočin Resistance to penetration by liquids Otpornost na propuštanje tekućina Widerstand gegen die durchdringung von Flüssigkeiten Resistenza dei materiali alla penetrazione dei liquidi	DIN EN ISO 811	48 cm
Zaščita tkanine Fabric protection Zaštita tkanine Stoffschutz Protezione tessuto	 QUICK CLEAN	preprosto odstranjevanje madežev easy stain removal lako uklanjanje mrlja einfache Fleckenentfernung facile rimozione delle macchie
	 M•PROTECT	vodoneprepustna membrana waterproof membrane vodonepropusna membrana wasserdichte Membran membrana impermeabile
Čiščenje / Nega / Cleaning / Pflege / Pulizia		    

Med barvnimi partijami so možna odstopanja. | Colours may vary between batches. | Moguća su odstupanja u boji kod proizvodnje.
Bei Farbpartien sind Farbabweichungen möglich. | Tra diversi lotti di produzione si possono riscontrare differenze cromatiche.

