

FLAVIA QC

SESTAVA COMPOSITION SIROVINSKI SASTAV ZUSAMMENSETZUNG COMPOSIZIONE		61% AKRIL, 36% POLIESTER, 3% VISKOZA 61% ACRYLIC, 36% POLYESTER, 3% VISCOSE 61% AKRIL, 36% POLIESTER, 3%, VISKOZA 61% ACRYL, 36% POLYESTER, 3% VISKOSE 61% ACRILICA, 36% POLIESTERE, 3% VISCOSA	
ŠIRINA WIDTH ŠIRINA BREITE ALTEZZA	140 cm $\pm 2\%$	TEŽA WEIGHT TEŽINA GEWICHT PESO	550 g/m ² $\pm 5\%$

TEST	STANDARD	REZULTAT/RESULTS/REZULTAT/ERGENIS/ RISULTATI	
		OSNOVA/WARP/ OSNOVA/KETTE / ORDITO	VOTEK/WEFT/ POTKA/SCHUSS / TRAMA
RAZTEZNA TRDNOST TENSILE STRENGTH ČVRSTOĆA NA RASTEZANJE ZUGFESTIGKEIT RESISTENZA ALLA TRAZIONE	EN ISO 13934-1	2525 N	1409 N
RAZTRŽNA TRDNOST TEAR GROWTH STRENGTH ČVRSTOĆA NA KIDANJE WEITERREISSFESTIGKEIT RESISTENZA ALLA LACERAZIONE	EN ISO 13937-3	355 N	388 N
DRSNOST NITI RESISTANCE TO SEAM SLIPPAGE OTPORNOST NA POMJERANJE /POMERANJE ŠAVA NAHTSCHIEBEWIDERSTAND RESISTENZA ALLO SCORRIMENTO DELLA CUCITURA	EN ISO 13936-2 PRI/AT/KOD/BEI/A 180 N	4,0 mm	0,7 mm
OBSTOJNOST TKANINE NA DRGNJENJE ABRASION RESISTANCE POSTOJANOST TKANINE NA TRLJANJE SCHEUERBESTANDIGKEIT RESISTENZA ALLA LACERAZIONE	EN ISO 12947-2	46.000 OBRATOV/REVS./OBRATAJA /TOUREN/GIRI	
PILING PILLING RESISTANCE PILING PILLBILDUNG RESISTENZA AL PILLING	EN ISO 12945-2 2.000 OBRATOV/REVS./OBRATAJA /SCHEUERTOUREN/GIRI	4-5	
OBSTOJNOST BARVE NA SVETLOBO COLOUR FASTNESS TO LIGHT POSTOJANOST BOJE NA SVJETLO/SVETLOST LICHTECHTHEIT RESISTENZA DEL COLORE ALLA LUCE	EN ISO 105-B02	4-5	
OBSTOJNOST BARVE NA DRGNJENJE COLOUR FASTNESS TO RUBBING POSTOJANOST BOJE NA TRLJANJE REIBECHTHEIT RESISTENZA DEL COLORE ALL'ABRASIONE	EN ISO 105-X12	SUHO/DRY/SUHO/ SUVO/TROCKEN / SECCO	MOKRO/WET/ MOKRO/NASS / UMIDO
		4-5	4-5
VSEBNOST AZO BARVIL CONTAIN OF AZO DYES SADRŽAJ AZO BOJA AZOFARBSTOFFE CONTENUTO DEI COLORANTI AZOICI	§ 64 LFGB 82.02-2,3,4	NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE	
VSEBNOST BARVIL, KI POVZROČAJO ALERGIJE ALERGY CAUSING DYES SADRŽAJ BOJA KOJE UZROKUJU ALERGIJE ALLERGISIERENDE FARBSTOFFE CONTENUTO DEI COLORANTI ALLERGENICI	DIN 54231:2005	NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE	
FORMALDEHID FORMALDEHYDE FORMALDEHID FORMALDEHYD FORMALDEIDE	EN ISO 14184-1	NI ZAZNANA NOT DETECTED NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE	

MERCIS

fabrics and leathers

TEST NEGORLJIVOSTI: FIRE RETARDANT: TEST NEGORIVOSTI: BRENNVERHALTEN: IGNIFUGO:	BS 5852 source 0	PRESTAL PASSED PROŠAO UEBERSTANDEN SUPERATO
---	---------------------	---

ZAŠČITA TKANINE: FABRIC PROTECTION: ZAŠTITA TKANINE: STOFFSCHUTZ: PROTEZIONE TESSUTO:	QUICK CLEAN QUICK CLEAN QUICK CLEAN QUICK CLEAN QUICK CLEAN
MED BARVNIMI PARTIJAMI SO MOŽNA ODSSTOPANJA V BARVI COLOUR DIFERENCES BETWEEN DYING LOTS ARE POSSIBLE MOGUĆA SU ODSUPANJA U BOJI KOD PROIZVODNJE FARBNIANSSEN SIND MOEGlich TRA I VARI LOTTI POSSONO VERIFICARSI DELLE VARIAZIONI NEL COLORE.	

