

BOLIVIA

SESTAVA ZGORNJE/SPODNJE TKANINE COMPOSITION SURFACE/BACK SIROVINSKI SASTAV GORNJE/DONJE TKANINE ZUSAMMENSETZUNG DER OBERE/UNTERE SEITE COMPOSIZIONE TESSUTO SUPERIORE/INFERIORE		100% POLIESTER / 90% POLESTER,10% BOMBAŽ 100% POLYESTER / 90% POLYESTER,10% COTTON 100% POLIESTERSKO VLAKNO / 90% POLIESTERSKO VLAKNO,10% PAMUK 100% POLYESTER / 90% POLYESTER,10% BAUMWOLLE 100% POLIESTERE / 90% POLIESTERE, 10% COTONE	
ŠIRINA WIDTH ŠIRINA BREITE ALTEZZA	140 cm +/-2%	TEŽA WEIGHT TEŽINA GEWICHT PESO	310 gr/m2 +/-5%


TEST	STANDARD	REZULTAT/RESULTS/REZULTAT/ERGEBNIS/ RISULTATI	
		OSNOVA/WARP/ OSNOVA/KETTE/OR DITO	VOTEK/WEFT/ POTKA/SCHUSS/TRAM A
RAZTEZNA TRDNOST TENSILE STRENGTH ČVRSTOČA NA RASTEZANJE ZUGFESTIGKEIT RESISTENZA ALLA TRAZIONE	i.A. EN ISO 13934-1	1408 N (37,3%)	1740 N (43,7%)
RAZTRŽNA TRDNOST TEAR STRENGTH ČVRSTOČA NA KIDANJE WEITERREISSFESTIGKEIT RESISTENZA ALLA LACERAZIONE	i.A. EN ISO 13937-3	154 N	148,9 N
DRSNOST NITI RESISTANCE TO SEAM SLIPPAGE OTPORNOST NA POMJERANJE /POMERANJE ŠAVA NAHTSCHIEBEWIDERSTAND RESISTENZA ALLO SCORRIMENTO DELLA CUCITURA	EN ISO 13936-2	4 mm	3,5 mm
OBSTOJNOST TKANINE NA DRGNJENJE ABRASION RESISTANCE POSTOJANOST TKANINE NA TRLJANJE SCHEUERBESTAENDIGKEIT RESISTENZA ALL'ABRASIONE	EN ISO 12947-1 EN ISO 12947-2	> 63.000 OBRATOV/REVS./OBRTAJA /TOUREN/GIRI	
PILING PILLING RESISTANCE PILING PILLBILDUNG RESISTENZA AL PILLING	EN ISO 12945-2 2.000 OBRATOV/REVS./OBRTAJA /SCHEUERTOUREN/GIRI	5	
OBSTOJNOST BARVE NA SVETLOBO COLOUR FASTNESS TO LIGHT POSTOJANOST BOJE NA SVJETLO/SVETLOST LICHTECHTHEIT RESISTENZA DEL COLORE ALLA LUCE	EN ISO 105-B02 Method 2	4	
OBSTOJNOST BARVE NA DRGNJENJE COLOUR FASTNESS TO RUBBING POSTOJANOST BOJE NA TRLJANJE REIBECHTHEIT RESISTENZA DEL COLORE ALL'ABRASIONE	EN ISO 105-X12	SUHO/DRY/SUHO/ SUVO/TROCKEN/ SECCO	MOKRO/WET/ MOKRO/NASS/UMIDO
		4-5	4-5
VSEBNOST AZO BARVIL CONTAIN OF AZO DYES SADRŽAJ AZO BOJA AZOFARBSTOFFE CONTENUTO DI COLORANTI AZOICI	§ 64 LFGB B 82.02-2,3,4,9	NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE	

MERCIS d.o.o., Puchova ulica 3, 1235 Radomlje, Slovenija ID: SI13107631

Tel. +386 1 4700700 Fax +386 1 4700720 e-mail:mercis@mercis.si

VSEBNOST BARVIL, KI POVZROČAJO ALERGIJE ALERGY CAUSING DYES SADRŽAJ BOJA KOJE UZROKUJU ALERGIJE ALLERGISIERENDE FARBSTOFFE CONTENUTO DI COLORANTI ALLERGENICI		NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE
TEST NEGORLJIVOSTI FIRE RETARDANT TEST NEGORIVOSTI BRENNVERHALTEN IGNIFUGO	acc. BS 5852 PART 1 Ignition source 0	PRESTAL PASSED PROŠAO UEBERSTANDEN SUPERATO
ZAŠČITA TKANINE: FABRIC PROTECTION: ZAŠTITA TKANINE: STOFFSCHUTZ: PROTEZIONE TESSUTO:	VODOODBOJNI NANOS WATER REPELLENT VODOODBOJNI NANOS WASSERABWEISEND IDROREPELENTE	

MED BARVNIMI PARTIJAMI SO MOŽNA ODSSTOPANJA V BARVI
COLOUR DIFFERENCES BETWEEN DYING LOTS ARE POSSIBLE
MOGUĆA SU ODSUPANJA U BOJI KOD PROIZVODNJE
FARBNIANSEN SIND MOEGlich
TRA VARI LOTTI DI TINTURA POSSONO VERIFICARSI DELLE VARIAZIONI NEL COLORE.



MERCIS d.o.o., Puchova ulica 3, 1235 Radomlje, Slovenija ID: SI13107631
Tel. +386 1 4700700 Fax +386 1 4700720 e-mail:mercis@mercis.si