

TIAGO

SESTAVA COMPOSITION SIROVINSKI SASTAV ZUSAMMENSETZUNG COMPOSIZIONE		54% AKRIL, 30% POLIESTER, 16% POLIPROPILEN 54% ACRYLIC, 30% POLYESTER, 16% POLYPROPYLENE 54% AKRIL, 30% POLIESTER, 16% POLIPROPILEN 54% ACRYL, 30% POLYESTER, 16% POLYPROPYLEN 54% ACRILICA, 30% POLIESTERE, 16% POLIPROPILENE	
ŠIRINA WIDTH ŠIRINA BREITE ALTEZZA	138 cm ± 2%	TEŽA WEIGHT TEŽINA GEWICHT PESO	680 g/m ² ± 5%

TEST	STANDARD	REZULTAT/RESULTS/REZULTAT/ERGEBNIS/ RISULTATI	
		OSNOVA/WARP/ OSNOVA/KETTE/ ORDITO	VOTEK/WEFT/ POTKA/SCHUSS/ TRAMA
RAZTEZNA TRDNOST TENSILE STRENGTH ČVRSTOĆA NA RASTEZANJE ZUGFESTIGKEIT RESISTENZA ALLA TRAZIONE	DIN EN ISO 13934-1	1995 N	1404 N
RAZTRŽNA TRDNOST TEAR STRENGTH ČVRSTOĆA NA KIDANJE WEITERREISSFESTIGKEIT RESISTENZA ALLA LACERAZIONE	DIN EN ISO 13937-3	227 N	209 N
DRSNOT NITI RESISTANCE TO SEAM SLIPPAGE OTPORNOST NA POMJERANJE /POMERANJE ŠAVA NAHTSCHIEBEWIDERSTAND RESISTENZA ALLO SCORCIMENTO DELLA CUCITURA	DIN EN ISO 13936-2 PRI/AT/KOD/BEI/AL PEZO 180 N	2 mm	1,5 mm
OBSTOJNOST TKANINE NA DRGNJENJE ABRASION RESISTANCE POSTOJANOST TKANINE NA TRLJANJE SCHEUERBESTAENDIGKEIT RESISTENZA TESSUTO ALL'ABRASIONE	DIN EN ISO 12947-1+ DIN EN ISO 12947-2	OBRATOV/REVS./OBRATAJA /TOUREN/GIRI >100.000	
PILING PILLING RESISTANCE PILING PILLBILDUNG RESISTENZA PILLING	DIN EN ISO 12945-2 2.000 OBRATOV/REVS./OBRATAJA /SCHEUERTOUREN/GIRI	5	
OBSTOJNOST BARVE NA SVETLOBO COLOUR FASTNESS TO LIGHT POSTOJANOST BOJE NA SVJETLO/SVETLOST LICHTECHTHEIT RESISTENZA ALLA LUCE	DIN EN ISO 105-B02	5	
OBSTOJNOST BARVE NA DRGNJENJE COLOUR FASTNESS TO RUBBING POSTOJANOST BOJE NA TRLJANJE REIBECHTHEIT RESISTENZA COLORI ALL'ABRASIONE	DIN EN ISO 105-X12	SUHO/DRY/SUHO/ SUVO/TROCKEN/ SECCO	MOKRO/WET/ MOKRO/NASS/UMIDO
		5	5
VSEBNOST AZO BARVIL CONTAIN OF AZO DYES SADRŽAJ AZO BOJA AZOFARBSTOFFE CONTENUTO DI COLERANTI AZOICI	§ 64 LFGB 82.02-2,3,4	NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE	
VSEBNOST BARVIL, KI POVZROČAJO ALERGIJE ALERGY CAUSING DYES SADRŽAJ BOJA KOJE UZROKUJU ALERGIJE ALLERGISIERENDE FARBSTOFFE CONTENUTO DI COLORANTI ALLERGENICI	DIN 54231	NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE	
TEST NEGORLJIVOSTI FIRE RETARDANT TEST NEGORIVOSTI BRENNVERHALTEN IGNIFUGO	BS 5852 part 1 Ignition source 0 DIN EN 1021-1 Without soaking	PRESTAL PASSED PROŠAO UEBERSTANDEN SUPERATO	

MERCIS

fabrics and leathers

KRČENJE PRI PRANJU SHRINKAGE AT WASHING SAKUPLJANJE KOD PRANJA EINLAUFWERTE RESTRINGIMENTO		OSNOVA/WARP/ OSNOVA/KETTE/ORDITO -2,5 %	VOTEK/WEFT/ POTKA/SCHUSS/TRAMA -3 %
--	--	---	---

MED BARVNIMI PARTIJAMI SO MOŽNA ODSSTOPANJA V BARVI
COLOUR DIFFERENCES BETWEEN DYING LOTS ARE POSSIBLE
MOGUČA SU ODSSTOPANJA U BOJI KOD PROIZVODNJE
FARBNIANSSEN SIND MOEGlich
TRA I VARI LOTTI POSSONO VERIFICARSI DELLE VARIAZIONI NEL COLORE.

