

STOCKHOLM WR

SESTAVA COMPOSITION SIROVINSKI SASTAV ZUSAMMENSETZUNG COMPOSIZIONE		50% POLIESTER, 24% BOMBAŽ, 12% VISKOZA, 14% LAN 50% POLYESTER, 24% COTTON, 12% VISCOSE, 14% LINEN 50% POLIESTER, 24% PAMUK, 12% VISKOZA, 14% LAN 50% POLYESTER, 24% BAUMWOLLE, 12% VISKOSE, 14% LEINEN 50% POLIESTERE, 24% COTONE, 12% VISCOSA, 14% LINO	
ŠIRINA WIDTH ŠIRINA BREITE ALTEZZA	140 cm $\pm 2\%$	TEŽA WEIGHT TEŽINA GEWICHT PESO	360g/m ² $\pm 5\%$

TEST	STANDARD	REZULTAT/RESULTS/REZULTAT/ERGENIS/ RISULTATI	
		OSNOVA/WARP/ OSNOVA/KETTE / ORDITO	VOTEK/WEFT/ POTKA/SCHUSS / TRAMA
RAZTEZNA TRDNOST TENSILE STRENGTH ČVRSTOĆA NA RASTEZANJE ZUGFESTIGKEIT RESISTENZA ALLA TRAZIONE	EN ISO 13934-1	1245 N	572 N
RAZTRŽNA TRDNOST TEAR GROWTH STRENGTH ČVRSTOĆA NA KIDANJE WEITERREISSFESTIGKEIT RESISTENZA ALLA LACERAZIONE	EN ISO 13937-3	50 N	29 N
DRSNOST NITI RESISTANCE TO SEAM SLIPPAGE OTPORNOST NA POMJERANJE /POMERANJE ŠAVA NAHTSCHIEBEWIDERSTAND RESISTENZA ALLO SCORRIMENTO DELLA CUCITURA	EN ISO 13936-2 PRI/AT/KOD/BEI/A 180 N	2,5 mm	3 mm
OBSTOJNOST TKANINE NA DRGNJENJE ABRASION RESISTANCE POSTOJANOST TKANINE NA TRLJANJE SCHEUERBESTANDIGKEIT RESISTENZA ALLA LACERAZIONE	EN ISO 12947-2	82.000 OBRATOV/REVS./OBRATAJA /TOUREN/GIRI	
PILING PILLING RESISTANCE PILING PILLBILDUNG RESISTENZA AL PILLING	EN ISO 12945-2 2.000 OBRATOV/REVS./OBRATAJA /SCHEUERTOUREN/GIRI	4	
OBSTOJNOST BARVE NA SVETLOBO COLOUR FASTNESS TO LIGHT POSTOJANOST BOJE NA SVJETLO/SVETLOST LICHTECHTHEIT RESISTENZA DEL COLORE ALLA LUCE	EN ISO 105-B02	4	
OBSTOJNOST BARVE NA DRGNJENJE COLOUR FASTNESS TO RUBBING POSTOJANOST BOJE NA TRLJANJE REIBECHTHEIT RESISTENZA DEL COLORE ALL'ABRASIONE	EN ISO 105-X12	SUHO/DRY/SUHO/ SUVO/TROCKEN / SECCO	MOKRO/WET/ MOKRO/NASS / UMIDO
		4	3
VSEBNOST AZO BARVIL CONTAIN OF AZO DYES SADRŽAJ AZO BOJA AZOFARBSTOFFE CONTENUTO DEI COLORANTI AZOICI	§ 64 LFGB 82.02-2,3,4	NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE	
VSEBNOST BARVIL, KI POVZROČAJO ALERGIJE ALERGY CAUSING DYES SADRŽAJ BOJA KOJE UZROKUJU ALERGIJE ALLERGISIERENDE FARBSTOFFE CONTENUTO DEI COLORANTI ALLERGENICI	DIN 54231	NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE	
FORMALDEHID FORMALDEHYDE FORMALDEHID FORMALDEHYD FORMALDEIDE	EN ISO 14184-1	NI ZAZNANA NOT DETECTED NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE	

MERCIS

fabrics and leathers

TEST NEGORLJIVOSTI: FIRE RETARDANT: TEST NEGORIVOSTI: BRENNVERHALTEN: IGNIFUGO:	BS 5852 source 0 EN 1021-1	PRESTAL PASSED PROŠAO UEBERSTANDEN SUPERATO
---	-------------------------------	---

ZAŠČITA TKANINE: FABRIC PROTECTION: ZAŠTITA TKANINE: STOFFSCHUTZ: PROTEZIONE TESSUTO:	VODOODBOJNI NANOS WATER REPELLENT VODOODBOJNI NANOS WASSERABWEISEND IDROREPELENTE
MED BARVNIMI PARTIJAMI SO MOŽNA ODSSTOPANJA V BARVI. COLOUR DIFERENCES BETWEEN DYING LOTS ARE POSSIBLE. MOGUĆA SU ODSUPANJA U BOJI KOD PROIZVODNJE. FARBUNTERSCHIEDE ZWISCHEN FARBPARTIEN SIND MÖGLICH. TRA IVARI LOTTI POSSONO VERIFICARSI DELLE VARIAZIONI NEL COLORE.	

