

LEVANA QC

SESTAVA COMPOSITION SIROVINSKI SASTAV ZUSAMMENSETZUNG COMPOSIZIONE		51% RECIKLIRAN OLEFIN, 27% POLIESTER, 22% AKRIL 51% RECYCLED OLEFIN, 27% POLYESTER, 22% ACRYLIC 51% RECIKLIRAN OLEFIN, 27% POLIESTER, 22% AKRIL 51% REZYKLIERTES OLEFIN, 27% POLYESTER, 22% ACRYL 51% RICICLATO OLEFIN, 27% POLIESTERE, 22% ACRILICA	
ŠIRINA WIDTH ŠIRINA BREITE ALTEZZA	140 cm ±2%	TEŽA WEIGHT TEŽINA GEWICHT PESO	550 g/m ² ±5%

TEST		STANDARD	REZULTAT/RESULTS/REZULTAT/ERGENIS/RISULTATI	
			OSNOVA / WARP / OSNOVA / KETTE / ORDITO	VOTEK / WEFT / POTKA / SCHUSS / TRAMA
RAZTEZNA TRDNOST TENSILE STRENGTH ČVRSTOĆA NA RASTEZANJE ZUGFESTIGKEIT RESISTENZA ALLA TRAZIONE		EN ISO 13934-1	2718 N	781 N
RAZTRŽNA TRDNOST TEAR GROWTH STRENGTH ČVRSTOĆA NA KIDANJE WEITERREISSFESTIGKEIT RESISTENZA ALLA LACERAZIONE		EN ISO 13937-3	274 N	122 N
DRSNOST NITI RESISTANCE TO SEAM SLIPPAGE OTPORNOST NA POMJERANJE / POMERANJE ŠAVA NAHTSCHIEBEWIDERSTAND RESISTENZA ALLO SCORRIMENTO DELLA CUCITURA		EN ISO 13936-2 PRI/AT/KOD/BEI/A 180 N	2,5 mm	1,6 mm
OBSTOJNOST TKANINE NA DRGNJENJE ABRASION RESISTANCE POSTOJANOST TKANINE NA TRLJANJE SCHEUERBESTAENDIGKEIT RESISTENZA ALLA LACERAZIONE		EN ISO 12947-2	45.000 OBRATOV/REVS./OBRATAJA /TOUREN/GIRI	
PILING PILLING RESISTANCE PILING PILLBILDUNG RESISTENZA AL PILLING		EN ISO 12945-2	2000 OBRATOV / REVS. /OBRATAJA / SCHEUERTOUREN / GIRI	5000 OBRATOV / REVS. /OBRATAJA / SCHEUERTOUREN / GIRI
			4	4
OBSTOJNOST BARVE NA SVETLOBO COLOUR FASTNESS TO LIGHT POSTOJANOST BOJE NA SVJETLO/SVETLOST LICHTECHTHEIT RESISTENZA DEL COLORE ALLA LUCE		EN ISO 105-B02	>5	
OBSTOJNOST BARVE NA DRGNJENJE COLOUR FASTNESS TO RUBBING POSTOJANOST BOJE NA TRLJANJE REIBECHTHEIT RESISTENZA DEL COLORE ALL'ABRASIONE		EN ISO 105-X12	SUHO / DRY / SUHO / SUVO / TROCKEN / SECCO	MOKRO / WET / MOKRO / NASS / UMIDO
			5	5
VSEBNOST AZO BARVIL CONTAIN OF AZO DYES SADRŽAJ AZO BOJA AZOFARBSTOFFE CONTENUTO DEI COLORANTI AZOICI		DIN EN 14362-1 DIN EN 14362-3	NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE	
VSEBNOST BARVIL, KI POVZROČAJO ALERGIJE ALLERGY CAUSING DYES SADRŽAJ BOJA KOJE UZROKUJU ALERGIJE ALLERGISIERENDE FARBSTOFFE CONTENUTO DEI COLORANTI ALLERGENICI		DIN 54231	NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE	
FORMALDEHID FORMALDEHYDE FORMALDEHID FORMALDEHYD FORMALDEIDE		EN ISO 14184-1	NI ZAZNANA NOT DETECTED NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE	
TEST NEGORLJIVOSTI FIRE RETARDANT TEST NEGORIVOSTI BRENNVERHALTEN IGNIFUGO		BS 5852 source 0 DIN EN 1021-1	PRESTAL PASSED PROŠAO UEBERSTANDEN SUPERATO	
ZAŠČITA TKANINE FABRIC PROTECTION ZAŠTITA TKANINE STOFFSCHUTZ PROTEZIONE TESSUTO	QUICK CLEAN			
MED BARVNIMI PARTIJAMI SO MOŽNA ODSTOPANJA V BARVI / COLOUR DIFERENCES BETWEEN DYING LOTS ARE POSSIBLE /MOGUĆA SU ODSTUPANJA U BOJI KOD PROIZVODNJE / UNTER DEN FARBPARTIEN SIND ABWEICHUNGEN MÖGLICH / TRA I VARI LOTTI POSSONO VERIFICARSI DELLE VARIAZIONI NEL COLORE.				

