

BOUCLE

WATER REPELLENT AND OIL REPELLENT

SESTAVA TKANINE COMPOSITION SIROVINSKI SASTAV TKANINE ZUSAMMENSETZUNG COMPOSIZIONE TESSUTO		100% POLIESTER 100% POLYESTER 100% POLIESTER 100% POLYESTER 100% POLIESTERE	
ŠIRINA WIDTH ŠIRINA BREITE ALTEZZA	140 cm +/-2%	TEŽA WEIGHT TEŽINA GEWICHT PESO	630 g/m ² +/-5%
TEST	STANDARD	REZULTAT/RESULTS/REZULTAT/ERGENIS/RISULTATI	
		OSNOVA/WARP/ OSNOVA/KETTE/ORDITO	VOTEK/WEFT/ POTKA/SCHUSS/TRAMA
RAZTEZNA TRDNOST TENSILE STRENGTH ČVRSTOČA NA RASTEZANJE ZUGFESTIGKEIT RESISTENZA ALLA TRAZIONE	EN ISO 13934-1	1286 N	1573 N
RAZTRŽNA TRDNOST TEAR STRENGTH ČVRSTOČA NA KIDANJE WEITERREISSFESTIGKEIT RESISTENZA ALLA LACERAZIONE	EN ISO 13937-3	134,9 N	344,4 N
DRSNOST NITI RESISTANCE TO SEAM SLIPPAGE OTPORNOST NA POMJERANJE /POMERANJE ŠAVA NAHTSCHIEBEWIDERSTAND RESISTENZA ALLO SCORRIMENTO DELLA CUCITURA	EN ISO 13936-2	4,0 mm	2,4 mm
OBSTOJNOST TKANINE NA DRGNJENJE ABRASION RESISTANCE POSTOJANOST TKANINE NA TRLJANJE SCHEUERBESTÄNDIGKEIT RESISTENZA ALL'ABRASIONE	EN ISO 12947-2	>100.000 OBRATOV/REVS./OBRATAJA /TOUREN/GIRI	
PILING PILLING RESISTANCE PILING PILLBILDUNG RESISTENZA PILLING	EN ISO 12945-2 2.000 OBRATOV/ REVS./OBRATAJA /SCHEUERTOUR EN/GIRI	4-5	
OBSTOJNOST BARVE NA SVETLOBO COLOUR FASTNESS TO LIGHT POSTOJANOST BOJE NA SVJETLO/SVETLOST LICHTECHTHEIT RESISTENZA ALLA LUCE	EN ISO 105-B02	>5	
OBSTOJNOST BARVE NA DRGNJENJE COLOUR FASTNESS TO RUBBING POSTOJANOST BOJE NA TRLJANJE REIBECHTHEIT RESISTENZA COLORE ALL'ABRASIONE	EN ISO 105-X12	SUHO/DRY/SUHO/ SUVO/TROCKEN/SECCO	MOKRO/WET/ MOKRO/NASS/UMIDO
		4	4
VSEBNOST AZO BARVIL CONTAIN OF AZO DYES SADRŽAJ AZO BOJA AZOFARBSTOFFE CONTENUTO DI COLORANTI AZOICI	§ 64 LFGB 82.02.2&3&4	NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE	
VSEBNOST BARVIL, KI POVZROČAJO ALERGIJE ALLERGY CAUSING DYES SADRŽAJ BOJA KOJE UZROKUJU ALERGIJE ALLERGISIERENDE FARBSTOFFE CONTENUTO DI COLORANTI ALLERGENICI	DIN 54231	NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE	
FORMALDEHID FORMALDEHYDE FORMALDEHID FORMALDEHYD FORMALDEIDE	EN ISO 14184-1	PRESTAL PASSED PROŠAO BESTANDEN SUPERATO	
TEST NEGORLJIVOSTI FIRE RETARDANT TEST NEGORIVOSTI BRENNVERHALTEN IGNIFUGO	DIN EN 1021-1 -without soaking- BS 5852 Source 0 -without soaking-	PRESTAL PASSED PROŠAO BESTANDEN SUPERATO	
ZAŠČITA TKANINE: FABRIC PROTECTION: ZAŠTITA TKANINE: STOFFSCHUTZ: PROTEZIONE TESSUTO:	VODOODBOJNI IN OLJEODBOJNI NANOS WATER REPELLENT AND OIL REPELLENT VODOODBOJNA I ULJE ODBOJNA OBRADA WASSER- UND ÖLABWEISEND IDRO E OLIO-REPELENTE		

MED BARVNIMI PARTIJAMI SO MOŽNA ODPANJA V BARVI.
COLOUR DIFFERENCES BETWEEN DYING LOTS ARE POSSIBLE.
MOGUĆA SU ODPANJA U BOJI KOD PROIZVODNJE.
FARBUNTERSCHIEDE ZWISCHEN FARBPARTIEN SIND MÖGLICH.
TRA I VARI LOTTI POSSONO VERIFICARSI DELLE VARIAZIONI NEL COLORE.

MERCIS

fabrics and leathers

